

BAUTHERM W

Expanded polystyrene thermal insulation panels.

Description

Expanded polystyrene. Certified plates for specific use in external thermal insulation systems (ETICS) in thicknesses of 3 to 10 cm. Coefficient of thermal conductivity: $\lambda = 0,036 \text{ W/mK}$

Technical Characteristics

Technical Charaxteristics	Normative	Unit	Symbol	Class	Value
Compressive strength	EN 826	kPa	CS(10)	-	80
Bending Strength	EN 12089	kPa	BS	-	125
Tensile strength perpendicular to faces	EN 1607	kPa	TR	-	200
Reaction to fire	EN 13501- 1	-	Euro-Class	E	E
Water absorption by total immersion	EN 16535	%	WL(T)	-	$\leq 2,5$
Water absorption by partial immersion	EN 16535	kg/m ²	WL(P)	-	$\leq 0,1$
Length	EN 822	mm	l	L(2)	± 2
Width	EN 822	mm	b	W(2)	± 2
Thickness	EN 823	mm	d	T(2)	± 2
Squareness on length and width per meter	EN 824	mm	S	S(2)	± 2
Flatness	EN 825	mm	P	P(3)	± 3

Thickness	Declared thermal conductivity	Thermal Resitance
d_N (mm)	λ_D (W/mK)	R_D (m ² K/W)
30.00	0.036	0.83
40.00	0.036	1.11
50.00	0.036	1.39
60.00	0.036	1.67
70.00	0.036	1,94
80.00	0.036	2.22
90.00	0.036	2.50
100.00	0.036	2.78

product user is held solely responsible for the result of application. No responsibility under any legitimate relationship can be substantiated against the company, based on the information set out hereunder. Product users are advised to refer to the latest revision of the technical manuals available at the official website of the product..

Other information

BAUER BUILDING TECHNOLOGIES
 Megara Industrial Estate, Attica
 Tel: 210 5744222
 Fax: 210 5740777
 Email: info@netbauer.com
 http// www.netbauer.com

Frankfurt, Reg. No 312310 QM
 Qualitätsmanagementsystem
 Zertifiziert nach DIN EN ISO 9001



Notes

Technical details, properties, recommendations and information on BAUER products are supplied in good faith. They are based on the company's research and experience, provided that they are stored and applied under normal conditions. As the method of using materials as well as project and environment conditions are beyond the control the company in each individual application setting, the